



TECHNICAL DATA

PROPERTY	VALUE	TEST METHOD
Nominal Density	± 2.2 Lbs./cu Ft. (Min)	ASTM D-1622-63
Closed Cell Content	95% by volume (min)	ASTM D-2856-70
Compressive Strength Parallel	52 psi min.	ASTM D-1621-73
Shear Strength Parallel	46 psi min.	ASTM O-273-61
Bond Strength	30 psi min.	ASTM O-297
Tensile Strength	70 psi min.	ASTM D-1623
K-factor	0.14 BTUhr./s.f./deg F Max Aged@77deg. F.	ASTM C-518-70
R-value	7.14 per 1 inch thick	ASTM C-518
Water Absorption	00.8 ins./sq.s.ft. (96 hours under 2 head)	ASTM D-2842-69
Water Vapor Transmission	1 perm - inches	ASTM C-355-64
Flammability	Flame spread 75 or less	ASTM E-84



ROMTECH CONSTRUCTION, INC.

Rm. 102 Liwig Bldg., 1258 Batangas St., Makati City

Tel. Nos.: 844-2516 / 843-4322 Fax: 888-0884

Branch Office: 7-B 4 Maria Cristina St., Cebu City Philippines

Tel Nos. (032) 254-2874 Telefax (032) 253-3445

Disclaimer: The use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven faulty, the manufacturer is not responsible for any loss or damage arising from incorrect usages.
Updated W/P 10 Dec2001